


# **TGG**



#### **DESCRIPTION**

TGG crystal, also known as terbium gallium garnet crystal, with the chemical formula Tb<sub>3</sub>Ga<sub>5</sub>O<sub>12</sub>, is a magne-to-optical crystal with good comprehensive properties. TGG crystal has a high magneto-optical constant, low optical loss, high thermal conductivity, and a high laser damage threshold. TGG single crystal is the best magne-to-optical material for Faraday polarizer and isolator, and the applicable wavelength is 400~1100nm (excluding 470~500nm). TGG (terbium gallium garnet) single crystal has a very high Verdet constant in the range of 400nm-1100nm (excluding 475-500nm), which is the best and most widely used magneto-optical material in Faraday rotators and isolators. By placing the rod of this material in a strong magnetic field, the Faraday rotation angle of more than 45° can be achieved. This allows the construction of a Faraday rotator as the main component of the Faraday isolator, which transmits light in only one direction.

#### **FEATURES**

- High damage threshold
- Low optical loss
- High thermal conductivity
- Large Verdet constant

#### **APPLICATIONS**

- Isolator
- Faraday rotator
- Magneto optic waveguide

#### CRYSTAL SPECIFICATION

Wavefront distortion	<λ/8 @632.8nm
Dimensional tolerance	Diameter: +0.0/-0.05 mm, length: ± 0.2mm
Extinction ratio	>30dB
Surface quality	10/5
Parallelism	<10"
Verticality	<5'
Clear aperture	>90%
Surface flatness	<λ/10 @632.8nm
Size	According to customer requirements
Coating	According to customer requirements



# **TGG**

### CRYSTAL PHYSICOCHEMICAL PROPERTIES

Attribute	Numerical value
Chemical formula	$Tb_3Ga_5O_{12}$
Lattice parameters	a=12.355Å
Growth mode	Lifting method
Density	7.13g/cm <sup>3</sup>
Mohs hardness	8
Melting point	1725℃
Refractive index	1.954@1064nm
Extinction ratio	30dB
Thermal conductivity	7.4 W cm <sup>-1</sup> k <sup>-1</sup>

## **SPECTROGRAM**

